



GOLD STONE

— DIGGING TO ACHIEVE YOUR NEEDS —

DOLOMITE LUMPS

Chemical Analysis:

Item	%
CaO	30% Max
MgO	20% Max
SiO ₂	1.2% Max
Fe ₂ O ₃	0.12% Max
Al ₂ O ₃	0.8% Max
TiO ₂	0.01%

Size: 5 -10 cm

Sieve Analysis of aggregates:

Sieve Size(mm)	Passing %
100mm	100 %
80mm	75 %
60mm	22 %
50mm	2 %
40 mm	1%

HQ Address: #536 Mohammed Nagib Axis, New Cairo 1, Cairo, Egypt. P.O: 11865

Factory Address: Block D #23 & 24, The Third Cell, The Third Sector, The Industrial Zone in Al-Matahra, Minya Governorate, Egypt.

Tel: +20 2 23278264 - +201032566099 - +201006278723

Email: export@goldstone.com.eg