



GOLD STONE

— DIGGING TO ACHIEVE YOUR NEEDS —

TALC SPECIFICATIONS

Chemical Analysis			
ITEM	Grade1	Grade 2	Grade 3
SiO ₂	60 - 62	60 - 61	53 - 58
MgO	31 - 32.5	30 - 31	28 - 30
Al ₂ O ₃	0.3 - 0.5	0.5 - 1.0	1 - 2
CaO	0.3 - 0.5	0.5 - 1.0	3 - 6
Fe ₂ O ₃	0.1 - 0.2	0.2 - 0.4	0.5 - 0.7
Na ₂ O	< 0.01	< 0.01	< 0.01
K ₂ O	< 0.01	< 0.01	< 0.01
L.O.I	4.5 – 5.0	5.5 – 6.5	8 – 9
P ₂ O ₅	0.01	0.02	0.04
H ₂ O	0.24	0.18	0.23
Mineralogical Analysis			
Asbestos free			
Physical Analysis			
Brightness	90%(min)	86%(min)	83%(min)
whiteness	90%(min)	86%(min)	83%(min)
Sp.gr	0.55	0.55	0.52
pH	7.00	7.20	7.56
Measured on (325 mesh) powder – 45 Micrometer			



HQ Address: #536 Mohammed Nagib Axis, New Cairo 1, Cairo, Egypt. P.O: 11865

Factory Address: Block D #23 & 24, The Third Cell, The Third Sector, The Industrial Zone in Al-Matahra, Minya Governorate, Egypt.

Tel: +20 2 23278264 - +201032566099

Email: export@goldstone.com.eg