GOLD STONE

DIGGING TO ACHIEVE YOUR NEEDS

QUARTZ SPECIFICATION

Chemical Analysis

ELEMENT	RESULT%
SiO2	99.0 - 99.7
TiO2	0.01 (max.)
AI2O3	0.01 - 0.2
Fe2O3	0.0 - 0.1
MnO	0.0 - 0.01
MgO	0.05 (max.)
CaO	0.1 - 0.7
Na2O	0.01 - 0.06
K2O	0.05 (max.)
P2O5	<0.01
L.O.l	0.12 - 0.35

Size: ***Run of mine or crushed from 1 to 15 cm max.***

And/or: According to customer requirements.

Lumps

HQ Address: #536 Mohammed Nagib Axis, New Cairo 1, Cairo, Egypt. P.O: 11865
Factory Address: Block D #23 & 24, The Third Cell, The Third Sector, The Industrial Zone in Al-Matahra, Minya Governorate, Egypt.
Tel: +20 2 23278264 - +201032566099 **Email:** export@goldstone.com.eg