



GOLD STONE
— DIGGING TO ACHIEVE YOUR NEEDS —

Egyptian rock phosphate

43.75% BPL-20.31% P₂O₅

Chemical Analysis

P₂O₅%	20.31
BPL %	43.75
Ca O	33.52
Mg O	1.46
Fe₂O₃	3.60
Al₂O₃	3.40
Cl	0.14
F	0.30
H₂O	1.43
SiO₂	5.24
CO₂	7.65
CaCO₃	18.00
Na₂O	0.56
K₂O	0.62
SO₃	1.76
Moisture	5.02
Organic Matter	1.64
Solubility in 2% Citric Acid`	30
Solubility in 2% Formic Acid	42
Solubility in 6% HCl Acid	51
T.C.P	57.23

Sieve Analysis

Size	%
4 Mesh	1.5
4-100 Mesh	77.6
100-200 Mesh	18.5
200-270 Mesh	1.4
-270 Mesh	1.0

Physical Properties

Fluidity	Free Flowing
-----------------	-------------------------

HQ Address: #536 Mohammed Nagib Axis, New Cairo 1, Cairo, Egypt. P.O: 11865

Factory Address: Block D #23 & 24, The Third Cell, The Third Sector, The Industrial Zone in Al-Matahra,
Minya Governorate, Egypt.

Tel: +20 2 23278264 - +201032566099

Email: export@goldstone.com.eg