



GOLD STONE

— DIGGING TO ACHIEVE YOUR NEEDS —

Egyptian rock phosphate

61.24% BPL-28.15% P₂O₅

Chemical Analysis

P₂O₅%	28.15
BPL %	61.24
Ca O	47.60
Mg O	0.32
Fe₂O₃	1.06
Al₂O₃	0.73
Cl	0.28
F	2.60
H₂O	2.27
SiO₂	6.87
CO₂	5.12
CaCo₃	14.00
Na₂O	0.48
K₂O	0.54
SO₃	1.23
Moisture	4.14
Organic Matter	1.15
Solubility in 2% Citric Acid`	32
Solubility in 2% Formic Acid	45
Solubility in 6% HCl Acid	65
T.C.P	61.18

Sieve Analysis

Size	%
4 Mesh	1.5
4-100 Mesh	77.6
100-200 Mesh	18.5
200-270 Mesh	1.4
-270 Mesh	1.0

Physical Properties

Fluidity	Free Flowing
-----------------	---------------------

HQ Address: #536 Mohammed Nagib Axis, New Cairo 1, Cairo, Egypt. P.O: 11865

Factory Address: Block D #23 & 24, The Third Cell, The Third Sector, The Industrial Zone in Al-Matahra, Minya Governorate, Egypt.

Tel: +20 2 23278264 - +201032566099

Email: export@goldstone.com.eg