



GOLD STONE

— DIGGING TO ACHIEVE YOUR NEEDS —

DOLOMITE POWDER

Chemical Analysis:

Item	%
CaO	32% Min
MgO	20% Min
SiO ₂	1.2% Max
Fe ₂ O ₃	0.12% Max
Al ₂ O ₃	0.8% Max
TiO ₂	0.01%
Whiteness	84%
Brightness	86%

Sieve Analysis

Sieve Size(Um)	Passing %
100 μ	100 %
70 μ	90 %
50 μ	25 %
30 μ	7 %
20 μ	1.2 %

150 Mesh = 100 μ

HQ Address: #536 Mohammed Nagib Axis, New Cairo 1, Cairo, Egypt. P.O: 11865

Factory Address: Block D #23 & 24, The Third Cell, The Third Sector, The Industrial Zone in Al-Matahra, Minya Governorate, Egypt.

Tel: +20 2 23278264 - +201032566099 - +201006278723

Email: export@goldstone.com.eg